

# Leben mit Holz!



elka -Holzwerke GmbH · Hochwaldstr. 44 · D-54497 Morbach

## Measurement table for natural wood panels 3-S, VITA

Standard dimensions: 505\*205 cm/505\*102.5 cm/252.5\*205 cm

These measurement tables are merely to be used for pre-dimensioning, precise static verification is still required !

Dimension: 505\*205cm/505\*102,5cm/252,5\*205 cm

Covering slat	Load in KN/m <sup>2</sup> , q <sub>k</sub>	1,0	1,5	2,0	2,5	3,0	3,5	4,0	4,5	5,0
		Panel strengths								
Field length in m										
5mm	15mm	0,89	0,78	0,71	0,66	0,62	0,59	0,56	0,54	0,52
	19mm	1,13	0,99	0,90	0,83	0,78	0,74	0,71	0,68	0,66
	22mm	1,23	1,07	0,97	0,90	0,85	0,81	0,77	0,74	0,71
	27mm	1,51	1,31	1,19	1,11	1,04	0,99	0,95	0,91	0,88
	32mm	1,74	1,52	1,38	1,28	1,20	1,14	1,09	1,05	1,02
9mm	27mm	1,51	1,31	1,19	1,11	1,04	0,99	0,95	0,91	0,88
	42mm	2,29	2,00	1,81	1,68	1,58	1,50	1,44	1,38	1,33
	50mm	2,66	2,32	2,11	1,96	1,84	1,75	1,67	1,61	1,55

  

Covering slat	Load in KN/m <sup>2</sup> , q <sub>k</sub>	1,0	1,5	2,0	2,5	3,0	3,5	4,0	4,5	5,0
		Panel strengths								
Field length in m										
5mm	15mm	1,20	1,04	0,95	0,88	0,83	0,79	0,75	0,72	0,70
	19mm	1,52	1,32	1,20	1,12	1,05	1,00	0,95	0,92	0,88
	22mm	1,64	1,43	1,30	1,21	1,14	1,08	1,03	0,99	0,96
	27mm	2,02	1,76	1,60	1,49	1,40	1,33	1,27	1,22	1,18
	32mm	2,33	2,04	1,85	1,72	1,62	1,53	1,47	1,41	1,36
9mm	27mm	2,02	1,76	1,60	1,49	1,40	1,33	1,27	1,22	1,18
	42mm	3,06	2,67	2,43	2,25	2,12	2,02	1,93	1,85	1,79
	50mm	3,56	3,11	2,83	2,63	2,47	2,35	2,24	2,16	2,08

  

Covering slat	Load in KN/m <sup>2</sup> , q <sub>k</sub>	1,0	1,5	2,0	2,5	3,0	3,5	4,0	4,5	5,0
		Panel strengths								
Field length in m										
5mm	15mm	1,10	0,96	0,87	0,81	0,76	0,73	0,69	0,67	0,64
	19mm	1,40	1,22	1,11	1,03	0,97	0,92	0,88	0,85	0,82
	22mm	1,52	1,32	1,20	1,12	1,05	1,00	0,95	0,92	0,89
	27mm	1,86	1,63	1,48	1,37	1,29	1,23	1,17	1,13	1,09
	32mm	2,15	1,88	1,71	1,59	1,49	1,42	1,35	1,30	1,26
9mm	27mm	1,86	1,63	1,48	1,37	1,29	1,23	1,17	1,13	1,09
	42mm	2,83	2,47	2,24	2,08	1,96	1,86	1,78	1,71	1,65
	50mm	3,29	2,88	2,61	2,42	2,28	2,17	2,07	1,99	1,92

  

Shear and creep deformations have not been taken into account!	$k_{mod}=0.8$	Calculation with:
Deflection $w_{inst}=L/300$	$\gamma_m=1.3$	EN 12369-3:2008
Field load is not taken into account!	KLED: medium	EN 1995-1-1
Characteristic load over the entire beam length!	$\gamma_{GQ}=1.45$	EN 13986:2004
The dead weight has not been taken into account and must be included!	NKL:2	

The table does not replace the static calculation in individual cases.  
 The manufacturer reserves the right to change that lead to technical improvement.  
 The data shown represent information not guarantee properties.

Date: 04.07.2016



**Sitz + Hauptverwaltung:**  
 D-54497 Morbach · Hochwaldstraße 44  
 Tel.: +49 (0) 65 33/9 56-0  
 Fax: +49 (0) 65 33/9 56-220  
 Email: info@elka-holzwerke.de  
 GLN: 42 505055 0000 0

**Geschäftsführer:**  
 Karl-Robert Kuntz, Gerd Michael Lersch  
 Registergericht Wittlich, HRB 42063  
 USt.-Id.-Nr. DE 811127378

**Bankverbindungen:**  
**Kreissparkasse Birkenfeld Kirn**, IBAN: DE75 5625 0030 0000 4108 10 · BIC: BILADE55  
**Postbank, Köln**, IBAN: DE76 3701 0050 0022 9505 03 · BIC: PBNKDEFF370  
**Commerzbank Idar-Oberstein**, IBAN: DE15 5624 0050 0150 2004 00 · BIC: COBADEFF562  
**CIC, Strasbourg**, IBAN: FR76 3008 7330 8500 0200 6930 113 · BIC: CMCIFRPP  
**Banque Populaire Lorraine Champagne, Sarreguemines**, IBAN: FR76 1470 7000 1008 7210 1875 584 · BIC: CC BP FR PP MTZ